

THERMAL AND ELECTROCHEMICAL PROCESS FOR METAL PRODUCTION

Cross Reference to Related Applications

5 This application claims the benefit of U.S. Provisional Application Serial No. 60/496,981, Filed August 20, 2003.

Statement Regarding Federally Sponsored Research or Development

 This invention was made with Government support under contract numbers W911QX-04-0009 awarded by the U.S. Army and MDA972-03-C-0034 awarded by the Defense
10 Advanced Research Projects Agency. The Government may have certain rights in the invention.


Field of the Invention

 The present invention relates to the production of metals. The invention has particular utility in connection with the production of titanium and will be described in connection with
15 such utility, although other utilities are contemplated, e.g., production of other high value multi-valence and high (2 or more) valence metals, in particular refractory metals such as chromium, hafnium, molybdenum, niobium, tantalum, tungsten, vanadium and zirconium which are given as exemplary.


Background of the Invention

20 The properties of titanium have long been recognized as a light, strong, and corrosion resistant metal, which has lead to many different approaches over the past few decades to extract titanium from its ore. These methods were summarized by Henrie [1]. Despite the many methods investigated to produce titanium, the only methods currently utilized

commercially are the Kroll and Hunter processes [2, 3]. These processes utilize titanium tetrachloride (TiCl_4) which is produced from the carbo-chlorination of a refined titanium dioxide (TiO_2) according to the reaction:




- 5 In the Kroll process [2] TiCl_4 is reduced with molten magnesium at $\approx 800^\circ\text{C}$ in an atmosphere of argon. This produces metallic titanium as a spongy mass according to the reaction:



from which the excess Mg and MgCl_2 is removed by volatilization, under vacuum at $\approx 1000^\circ\text{C}$. The MgCl_2 is then separated and recycled electrolytically to produce Mg as the

- 10 reductant to further reduce the TiCl_4 . In the Hunter process [3,4] sodium is used as a reductant according to the reaction:



The titanium produced by either the Kroll or Hunter processes must not only be separated from the reductant halide by vacuum distillation and/or leaching in acidified solution to free
15 the titanium sponge for further processing to useful titanium forms, but also require the recycling of the reductant by electrolysis. Because of these multiple steps the resultant titanium is quite expensive which limits its use to cost insensitive applications.

- The US Bureau of Mines performed extensive additional investigations [1,5-8] to improve the Kroll and Hunter processes. Many other processes have been investigated that
20 include plasma techniques [9-13], molten chloride salt electrolytic processes [14], molten fluoride methods [15], the Goldschmidt approach [16], and alkali metal-calcium techniques [17]. Other processes investigated have included aluminum, magnesium, carbothermic and carbo-nitrothermic reduction of TiO_2 and plasma reduction of TiCl_4 [18] without measurable


success. Direct reduction of TiO_2 or TiCl_4 using mechanochemical processing of ball milling with appropriate reductants of Mg or calcium hydride (CaH_2) also have been investigated [19] without measurable success. Kroll, who is considered as the father of the titanium industry [20] predicted that titanium will be made competitively by fusion electrolysis but to date, this
5 has not been realized.

An electrolytic process has been reported [21] that utilizes TiO_2 as a cathode and carbon or graphite as the anode in a calcium chloride electrolyte operated at 900°C . By this process, calcium is deposited on the TiO_2 cathode, which reduces the TiO_2 to titanium and calcium oxide. However, this process is limited by diffusion of calcium into the TiO_2 cathode
10 and the build-up of calcium oxide in the cell, which limits operating time to remove the calcium oxide or replacement of the electrolyte. Also the TiO_2 cathode is not fully reduced which leaves contamination of TiO_2 or reduced oxides such as TiO , mixed oxides such as calcium titanate as well as titanium carbide being formed on the surface of the cathode thus also contaminating the titanium. Thus, current TiO_2 cathode electrolytic processes are no
15 more commercially viable than the electrolytic processes before it.


Summary of the Invention

The instant invention is a combination of a thermal and an electrochemical process, which utilizes a carbon or composite anode containing a metal oxide of a metal of interest, as a feed electrode. As used herein the term “carbon” is meant to include carbon in any of its
20 several crystalline forms including, for example, graphite. For example, for producing purified titanium, the feed should comprise TiO_2 which may be high purity, rutile, synthetic rutile, illuminate or other source of titanium, mixed with a source of carbon and pressed together with or without a binder that also may be a source of carbon on pyrolysis to form a

TiO₂-C composite green electrode or billet. The TiO₂-C composite billet is then heated, in the absence of air to avoid oxidation of the carbon component, to a temperature sufficient to reduce the plus four valence of the titanium in the TiO₂ to a lower valence. The temperature of heating and time at temperature will determine the reduced oxide stoichiometry of the titanium oxide which may be expressed as Ti_xO_y where the ratio of y/x can be 0 to equal or less than 2 and y balances the valence charge of the titanium species. Some examples of reduced titanium oxide compounds include TiO, Ti₂O₃, Ti₃O₅, and Ti₄O₇ and mixtures thereof. Sufficient residual carbon needs to remain after the thermal reduction step or can be added separately to stoichiometrically react with the reduced titanium oxide to electrochemically produce titanium at the cathode and CO₂ and/or CO at the anode. The reduced titanium state oxide composite anode overall general reactions are:




at the anode:



where 2y/x is the oxide state of the titanium in the electrolyte,

at the cathode:



Brief Description of the Drawings

Further features and advantages of the present invention will be seen by the following detailed description, taken in conjunction with the accompanying drawings wherein:

Fig. 1 is a diagrammatic illustration schematically illustrating an electrochemical reaction according to the present invention;

Fig. 2a is a diagrammatic illustration of electrochemical process of the present invention;

Fig. 2b is a diagrammatic illustration of an electrochemical cell and process in accordance with the present invention;

5 Fig. 3 is a view similar to Fig. 2b providing further details of an electrochemical cell in accordance with the present invention;

Fig. 4 is a perspective view showing details of an electrode in accordance with the present invention;

10 Fig. 5 is a graph illustrating surface resistivity of a titanium oxide carbon anode over time.


Detailed Description of the Invention

The present invention employs a novel electrochemical system for producing titanium and other metals by a combination of thermal and electrochemical processes from a novel metal oxide-carbon composite anode. More particularly, the present invention produces
15 purified titanium or other metal powders by a thermal/electroreduction composite anode process using a metal oxide-carbon anode in a molten salt electrolyte.

Heretofore the electrolysis of titanium oxide (TiO_2) has not been successful because TiO_2 has little to no solubility in molten salt electrolytes which is also true of other titanium compounds. Titanium tetrachloride (TiCl_4) is a covalent compound that has limited solubility
20 in fused salts and does not readily form complexes with other inorganic salts. It also is highly volatile and is quickly lost from most fused salts. However, since titanium is multivalent, it has been shown that TiCl_4 could be reduced to lower valent ionic species of Ti^{+3} and Ti^{+2} , which do show some solubility in some molten salts. However, because of secondary

reversibility reactions, which lead to loss in current efficiency and poor quality of metal, heretofore no practical process has evolved for electrowinning titanium from a TiCl_4 feed. Investigations of separating the anolyte and catholyte to avoid alternating oxidation and reduction with low current efficiency have not proven successful on a commercial scale.

5 Since titanium +3 (corresponding to y/x of 1.5) and titanium +2 (corresponding to y/x of 1.0) are ionic species, it should be possible to deposit titanium at the cathode, i.e. according to the reactions:



from a molten salt electrolyte. However, such reactions have not been demonstrated
10 commercially since heretofore there has not been demonstrated an acceptable process to continuously supply $\text{Ti}^{+2y/x}$ or lower valence ions where y/x is less than 2 to a molten salt electrolyte. The present invention in one aspect provides a metal oxide/carbon composite anode containing Ti_xO_y in which a high valence metal such as Ti^{+4} , is thermally reduced to a valence less than +4, and is used to provide a continuous supply of reduced titanium ions to a
15 molten salt electrolyte. The oxygen combines with the carbon in the anode to produce CO_2 and/or CO gas. Any excess carbon in the anode floats to the top of the molten salt electrolyte where it periodically can be skimmed if necessary and does not interfere with the continuous electrolysis process.

It is well established that thermal reduction is much more economical than
20 electrochemical reduction. Therefore reducing TiO_2 thermally is more economical than electrolytically reducing in a composite anode of TiO_2 -carbon. If TiO_2 is heated with carbon, carbo-thermic reduction will proceed based on the thermodynamic prediction and kinetics of the reactants. For example it has been found when the proper proportions of TiO_2 and carbon

are heated to various temperatures, reduced oxides are produced. An example reaction is $2\text{TiO}_2 + \text{C} = \text{Ti}_2\text{O}_3 + \text{CO}$. The Ti_2O_3 in which the titanium is in a +3 valence state can be produced over the temperature range of 1250-1700°C. Since the product is a solid Ti_2O_3 and gaseous CO if the pressure is reduced the kinetics of the reactions is enhanced.

5 It is also possible to produce the suboxide TiO according to the reactions $\text{TiO}_2 + \text{C} = \text{TiO} + \text{CO}$ or $\text{Ti}_2\text{O}_3 + \text{C} = 2\text{TiO} + \text{CO}$. Either reaction will be enhanced at reduced pressure. Titanium in TiO is in the +2 valence state. A competing reaction is $\text{TiO}_2 + 3\text{C} = \text{TiC} + 2\text{CO}$ or $\text{Ti}_2\text{O}_3 + 5\text{C} = 2\text{TiC} + 3\text{CO}$. When the suboxide is used as a feed for the composite anode, the lowest valence is the most desirable. Thus it is desirable to prevent TiC forming in which the
10 titanium is in a +4 state. It has been found that TiO can be produced at a reaction temperature above 1700°C if the pressure is reduced to 0.01 atmosphere or lower. If the pressure is as high as 0.1 atmosphere a reaction temperature above 1800°C is required to produce TiO free of TiC. At atmospheric pressure a reaction temperature above 2000°C is required to produce TiO free of TiC.

15 In addition to producing titanium from a composite anode consisting of a reduced titanium oxide and a carbon source referred to as a composite anode it is also possible to electrowin titanium from other titanium compounds that are not oxides. These compounds include titanium nitride (TiN). Titanium nitride is a conductor and does not require any conductive phase such as carbon with titanium suboxides. TiN can be produced by reacting
20 $\text{TiO}_2 + 2\text{C} + \text{N} = \text{TiN} + 2\text{CO}$. The TiN is pressed and sintered in a nitrogen atmosphere to produce a solid of TiN. The TiN can then be utilized as an anode in a fused salt to electrowin/deposit titanium at the cathode and nitrogen gas will be evolved at the anode.

Another compound is titanium carbide (TiC). Titanium carbide is produced by the

reaction of $\text{TiO}_2 + 2\text{C} = \text{TiC} + 2\text{CO}$. The TiC is a conductor and when TiC particles are pressed and sintered to a solid, the solid can serve as an anode. When using TiC as the anode a separator or diaphragm should separate the cathode and anode compartments. Titanium ions will be electrolytically dissolved from the anode and reduced to titanium metal at the cathode.

5 The released carbon will be in solid form and must be accounted for in an overall materials balance. To account for the carbon the anode can be depolarized with oxygen wherein the oxygen will react with the carbon to form gaseous CO_2 and/or CO . Thus oxygen gas would be passed over the anode to react with the carbon, but since titanium is so sensitive to oxygen the cathode should be separated from the anode with a diaphragm to prevent the oxygen from
10 contacting the deposited titanium.

It is taught in WO09964638, US6,663,763B2, WO 02/066711 A1, WO 02/083993 A1 and WO03/002 785 A1, that TiO_2 can serve as a cathode in a calcium chloride fused salt wherein the TiO_2 is reduced to titanium metal with oxygen given off at the anode using an inert anode or CO_2/CO using a carbon/graphite anode. Those teachings do not consider
15 reduced or suboxides of titanium which require less electrochemical energy to produce titanium metal than required to reduce TiO_2 . Thus the reduced oxides of Ti_2O_3 or TiO can serve as cathodes and be electrochemically reduced in molten calcium chloride or other molten salt electrolytes.

Heretofore, there has not been an electrochemical system to produce titanium similar
20 to electrowinning aluminum in which alumina (Al_2O_3) is soluble in molten cryolite (NaAlF_4) which under electrolysis produces aluminum metal with CO_2/CO being given off at a carbon anode, because there has not been identified a molten salt composition that will dissolve TiO_2 . There is no known molten salt compound or combination of compounds that will dissolve

TiO₂. However, there are molten salt compositions that will dissolve the reduced the suboxide TiO which is an ionic compound that is very electrically conductive. For example TiO is soluble in molten calcium chloride mixed alkali and alkaline earth chlorides as well as fluorides or mixed chlorides and fluorides. Thus TiO can be dissolved in CaCl₂ or other salt mixture, and using a carbon/graphite anode electrolyzed to produce titanium at the cathode and CO₂/CO at the anode or oxygen using an inert anode. Since titanium is sensitive to oxygen a separator or diaphragm should be used between the anode and cathode.

It is well know that the higher the temperature of a solvent the greater the solubility of the solute. In this case the higher the molten salt temperature the greater the solubility of a titanium suboxide such as TiO or Ti₂O₃. In the previous discussions the operating salt temperatures are below that of the melting point of titanium and thus titanium is deposited as a solid in a particulate morphology. As in the case of electrowinning aluminum in which aluminum oxide is soluble in cryolite at over 900°C, the aluminum is in a molten state and thus more easily separated from the molten salt/cryolite. In order to achieve the same advantage with titanium, the molten salt operating temperature should be above the melting point of titanium or about 1670°C. Molten salts that have high melting temperatures that will not readily vaporize at 1670°C or slightly above include calcium fluoride (CaF₂) 1360°C, and barium fluoride BaF₂ 1280°C. It was found the titanium suboxides and particularly TiO is quite soluble in CaF₂ at temperatures above 1670°C. Thus titanium is readily electrowon from its suboxides dissolved in CaF₂ or other salts above 1670°C using a carbon/graphite anode that produces CO and CO₂ on electrolysis or an oxygen stable anode that produces oxygen on electrolysis. The titanium produced above 1670°C is in a molten state and thus readily separatable from the molten salt whose density is less than 3.0 g/cc at the operating

temperature and titanium is approximately 4.0 g/cc at the operating temperature thus causing the titanium to sink for easy separation.

Referring to Fig. 1, there is illustrated schematically the formation of a metal oxide-carbon composite anode in accordance with the present invention. Titanium oxide in a particle size of 0.001 - 1000 microns, preferably 0.01 - 500 microns, more preferably 0.1 to 10 microns, is mixed with carbon flakes of average particle size 0.001 - 1000 microns, preferably 0.01 - 100 microns, more preferably 0.01 to 1 microns, in a weight ratio of TiO_2 to carbon of 7:1 to 4:1 using a ball mill mixer. The TiO_2 powder and carbon flakes were mixed dry, or optionally with a binder, in a ball mill mixer for 4-24 hours. The resulting TiO_2 powder/carbon flake mix was pressed in a steel die to form a mechanically stable green electrode or billet. The billet was then placed in an oven, and heated in the absence of air to 1000 to 2200°C, preferably about 1100°C to 1800°C, for 0.1 to 100 hours, preferably about two hours, to form a titanium suboxide/carbon composite electrode.

Referring to Figs. 2 and 2a, the titanium oxide/carbon composite electrode 20 made as above described is employed as an anode in an electrochemical cell 22 with a conventional metallic, e.g., steel electrode 24, and an alkali metal molten salt electrolyte 26.


The composition of the molten salt electrolyte 26 used in the cell 22 has an effect on the titanium produced at the cathode. The electrolyte should comprise a strong Lewis acid formulation such as NaAlCl_4 , which melts as low as 150°C, optionally containing fluoride additions such as an alkali fluoride and/or potassium titanium fluoride with the reduced state Ti_xO_y -C anode. Other useful electrolyte compositions include binary, tertiary, and quaternary alkali and alkaline earth chlorides, fluorides and mixed chloride-fluorides with melting point temperatures in the 300-900°C range. For producing titanium preferred electrolytes include

NaCl - CaCl_2 -KCl in a mole ratio of 50:50:20; NaCl-LiCl-KCl in a mole ratio of 20:60:40; AlCl_3 - NaCl - NaF in a mole ratio of 70:30:20 LiCl-KCl eutectic with 20 wt% NaF, eutectic of LiF-KF, etc. Moreover, the polarizing strength of the cation will directly affect the electroreduction of electrocrystallization to titanium. And, the small highly ionic strength and steric effect of e.g., a lithium ion in the electrolyte enhances the polarizing strength at the cathode and thus the electroreduction of titanium. Other such highly ionic ions can aid in stabilizing the Ti^{+3} and/or Ti^{+2} ions in the molten salt electrolyte as well as their electroreduction at the cathode.

To avoid disproportionation during the electrolysis between titanium in the metallic state, that is electrowon titanium, and higher titanium ions such as Ti^{+3} , it is preferable to have only Ti^{+2} ions in solution which as they are reduced to the metal are replaced with other Ti^{+2} ions from the anode thus requiring TiO in the anode. Thus desirably the fused salt initially contains Ti^{+2} ions which desirably is in the concentration range of ½ to 20%, more desirably in range of 1 to 10% and most desirably in the range of 2 to 8%.

The anion also can have an influence on the steric and solvent effect of the titanium species, which also influences the titanium deposit at the cathode. For example, the Ti-F bond is stronger than the Ti-Cl bond, which brings about an increase in the activity of the titanium ions in the molten salt electrolyte and consequently the morphology of the titanium deposited at the cathode. The anion and the titanium ion complex effects the number of crystallization centers available on the cathode and thus the morphology of the titanium cathode deposit. The complex TiF_6^{-3} and the TiF_6^{-2} anion is known and can be directly reduced to titanium. Mixed anions are also known, such as $\text{TiF}_{6-N} \text{Cl}_N^{-3}$. A strong Lewis acid

thus stabilizes and increases the activity of the titanium ion. While not wishing to be bound by theory, it is believed that the reactions proceed as follows:



and at the anode Ti^{+3} ions are released from the composite anode to produce the TiF_6^{-3} . Thus

5 titanium is directly reduced from the +3 valence to the metal. Because titanium is multivalent it is also possible that Ti^{+3} is reduced to Ti^{+2} and then to the metal Ti^0 . However, as stated above, if all titanium ions in solution are in the +2 valence then the reduction is $\text{Ti}^{+2} + 2\text{e} = \text{Ti}^0$.

Based on this analysis alkali fluorides may be regarded as stabilizing agents in
10 chloride molten salt electrolytes. Thus the ratio of F/Cl and/or Ti/F will have an effect on the electroreduction of titanium. Indeed it has been demonstrated that all chloride molten salt electrolytes produce small and/or dendritic deposits of titanium. As fluorides are added to the molten salt electrolyte the morphology of the deposit changes to larger and coherent particulate deposits. As the electrolyte changes to primarily or all fluoride, the titanium
15 deposits become flaky to a fully adherent film. The major morphology change begins at a F/Cl ratio of approximately 0.1 and solid films become possible at a ratio of approximately 1.0.

The morphology and size of the titanium deposit is also influenced by the current density of the cathode. The higher the current density the smaller the particle size. Typical
20 cathode current densities are in the 0.05 to 5 amperes/cm² range. The most desirable cathode current densities are in the 0.1 to 2.0 amperes/cm² range, and the preferred cathode current densities are in the 0.25 to 1 amperes/cm² range, depending on the morphology of the titanium desired at the cathode. It also has been found that very high current densities can be

used at the cathode under high mass flow of the electrolyte and the use of the composite anode. By moving the electrolyte over the cathode surface via gas bubbling or pumping at a fast rate it is possible to electrolytically produce titanium particulate up to cathode current densities of 125 amps/cm².

5 It also has been found that pulsing the current affects the morphology, particle size and cathodic efficiency. The current can be pulsed to on and off sequences in various wave forms such as square, sinusoidal, etc. as well as periodically alternating the polarity. It was found pulsing the current produced more coherent deposits and larger particles as well as solid films on the cathode. It was also found periodically reversing the polarity between two composite
10 electrodes produced titanium within the electrode. That is the Ti_xO_y in the electrode was reduced to titanium, which remained as a solid agglomerate of titanium particles in the same form of the original composite electrode.

A bench scale electrolytic cell for producing titanium in accordance with the present invention is illustrated in Fig. 3. The cell 30 comprises a cylindrically shaped steel walled
15 vessel 32 having a funnel-shaped bottom closed by a valve 36. The vessel walls 32 are wrapped in a resistance heater (not shown) which in turn is covered by thermal insulation 40. A porous basket 42 formed of carbon fiber mesh is suspended within container 30 and is connected via an anode connector 44 to the plus side of the DC current source. Wall 32 of the steel vessel is connected via a conductor 46 to the negative side of a DC current source.
20 Basket 42 is loaded with pellets or discs 48 of titanium suboxide - carbon flake anode material made as above described. The cell is filled with a molten salt electrolyte (60:LiCl - 40KCl) the cell is sealed with a top 50, swept with argon purge to remove air, and voltage of 3 applied which resulted in precipitation of dendritic titanium sponge particles. The titanium sponge

particles were then removed via valve 36, separated from the electrolyte, and found to have a purity of 99.9%.

It is possible to deposit other metals similarly. For example, by using a composite anode which includes other metal oxides in addition to the Ti_xO_y , it is possible to produce an alloy of titanium. For example, an alloy of Ti-Al-V can be produced by mixing aluminum oxide, vanadium oxide and TiO_2 with carbon to form the anode whereby to produce alloy particulate or solid films of Ti-Al-V. The E_0 and current density should be adjusted to deposit precise composition alloy particles. Other metals or alloys can be produced by incorporating other metal oxides in the anode in accordance with the present invention.

From a practical commercial standpoint of producing titanium particulate in which the particulate can be used directly in powdered metallurgical fabrication or consolidated into billets for subsequent rolling into sheet, forging, etc. it is desirable to produce the particulate at as low cost as possible. High mass transfer and high current density that produces particle sizes that are desirable for commercial applications can be achieved in a cell configuration such as shown in Figure 4.

In this case the anode container can be a porous carbon-carbon or other anodic container in which Ti_xO_y -C anode segments 60 are placed, and the structural container can be the cathode and/or a cathode 62 placed inside the structural container (not shown). Preferably the container is insulated to maintain heat in the molten salt electrolyte to achieve thermal neutrality with the IR/joule heating of the electrolyte at high current densities. Also if desired the molten salt electrolyte could be pumped through cyclone systems and filters to continuously collect the titanium particulate as it is being produced. Commercial pumping systems are readily available to handle pumping molten salt electrolytes such as used in the

aluminum and mass soldering industries to pump molten metals. Molten salt electrolytes that are desirable for high mass transfer cell designs of which Figure 4 is just one example, include strong Lewis acid compositions such as NaAlCl_4 and fluoride compositions, and fluoride or chloride alkali and alkaline earth metal salts and mixtures thereof. Utilizing a high mass transfer cell design in which the molten salt electrolyte is pumped over the cathode surface, with high stirring rates and/or ultrasonics to agitate the molten salt electrolyte or the cathode itself coupled with a reduced valence $\text{Ti}_x\text{O}_y\text{-C}$ anode permits production of titanium particulate at a relatively high rate and relatively low cost. And current pulsing as well as periodic reversing the current can further enhance the production of titanium particulates when coupled with a high mass transfer rate cell as above described.

Heretofore aluminum and magnesium have been produced by a composite anode process utilizing anodes of $\text{Al}_2\text{O}_3\text{-C}$ or MgO-C [23-26]. However, there is no teaching or suggestion in any of the prior art that recognizes that high valence (4 or more) or multi-valence metals could be produced by a composite anode process. More importantly, it was not recognized that high value high valence or multi-valence metals such as titanium, chromium, hafnium, molybdenum, niobium, tantalum, tungsten, vanadium, and zirconium could be produced utilizing a composite anode, as in the present invention. Neither was it recognized that a high valence metal oxide could be thermally reduced to a lower valence state in a composite anode or that a reduced valence state metal oxide-carbon anode could be used to produce particulate metal by electroreduction.

In contrast to producing a molten metal aluminum (melting point approx. at 660°C) and magnesium (melting point approx. at 650°C), the present invention permits control of particle geometry and size, and grain size in the particle can be controlled by the molten salt

composition, its operating temperature and the cathode current density. Moreover, the instant invention permits direct production of metals in the powdered/particulate solid state, unlike the prior art processes which produced molten aluminum [23, 25, 26] or magnesium [24].

In addition, the combination of thermal treatment to reduce the metal to a lower
5 valence state, the use of carbon in the anode to release a lower valence state metal into the molten salt, and the selection of molten salt to stabilize the lower valence state metal so as to produce a fully reduced metal at the cathode, is a unique and advantageous feature of the current invention.

An alternative to reducing the titanium valence in the molten salt is to depolarize the
10 cathode using hydrogen which could not only prevent the re-oxidation of the lower valence titanium at the anode and reduce the total cell voltage, but also allow for the formation of titanium hydrides at the cathodes. Titanium hydride is much more stable than titanium toward oxidation. The present invention thus permits the production of very low oxygen titanium.

Moreover, the present invention overcomes a problem of poor electrical conductivity
15 of the metal oxide-carbon anode of my previous composite anode process [23-26] which required the use of aluminum or magnesium metal conductors through the composite anode to carry current and prevent high voltage drops due to the poor electrical conductivity of the $\text{Al}_2\text{O}_3\text{-C}$ or MgO-C composite anodes. In the instant invention, poor anode electrical conductivity is overcome by using highly electrically conductive carbon flake as the major
20 carbon source in the composite anode. Small size composite anode pieces can also be utilized to reduce voltage drop as illustrated in Figure 3 as contrasted to large size anodes which can result in high resistivity and larger voltage drops that increase energy consumption. Examples of low resistivity in a reduced valence state titanium oxide carbon anode is shown in Figure 5.

Further when the TiO_2 is reduced to TiO , the TiO is very electrically conductive, more so than graphite. Thus anodes made with TiO are quite conductive and in one iteration does not require pressing into a composite with graphite flake or other carbon forms. The TiO is so conductive, it can be simply mixed with carbon/graphite in a basket that serves as the anode
5 with a conductor which can be the basket or a graphite rod.

The following non-limiting Examples will further demonstrate the present invention.

Example 1

Titanium dioxide (TiO_2) with a purity of 99% in a particle size of 0.3 microns was mixed with graphite flake in a particle size of 40 microns in a ratio of 80 grams of TiO_2 and
10 20 grams of graphite flake using a ball mill mixer. The resulting TiO_2 -graphite flake mixture was pressed in a steel die at 50,000 psi, which provided a mechanically stable billet without any binder system. The TiO_2 -graphite flake billet was heated to 1100°C in the absence of air for two hours. An XRD analysis showed the resulting composite anode to consist of Ti_2O_3 , Ti_3O_5 and Ti_4O_7 and graphite. The resulting titanium oxide-graphite composite anode was cut
15 into one inch (2.54 cm) long segments, and the segments placed in a carbon-carbon composite basket as illustrated in Fig. 3 which had residual porosity that served as a membrane and to which the positive terminal of a dc power supply was connected. A steel walled container (illustrated in Fig. 3) was used to melt an electrolyte consisting of NaCl - CaCl_2 - KCl eutectic at a temperature of 650°C . The steel walled container was connected to the negative terminal
20 of the dc power supply. The steel walled container was covered, sealed and swept with an argon purge to remove any air from the system. Electrolysis was conducted at an anode and cathode current density of 0.5 amps/cm^2 , which produced titanium particulate at the steel cathode. The titanium particulate was harvested with a screen scoop and then subjected to

1200° C in a vacuum to remove all traces of the electrolyte. The particle size was in the range of one to ten microns with a predominance of 5-10 microns. The titanium powder was analyzed for oxygen and found to have 800 parts per million. The current efficiency was measured by calculating the ampere hours passed and weighing the titanium produced which
5 was found to be 95% at the cathode and 99% at the anode.

Example 2

A mixture of TiO_2 and graphite flake was mixed as described in Example 1 and a resin binder of phenolic was used to bind the particles in the pressing operation. The pressed body was then heated in an inert atmosphere to 1300°C, which produced a well-bonded strong
10 composite anode consisting of a mixture of Ti_2O_3 with some Ti_3O_5 and a small amount of TiC along with graphite. Electrolysis was conducted as in Example 1 at a cathode current density of 1.0 amp/cm². Titanium powder was produced at an efficiency of 90% in an average particle size of 10 microns.

Example 3

15 Example 2 was repeated with electrolysis at a cathode current density of 0.25 amps/cm² which produced an efficiency of 97% with a particle size of approximately 20 microns.

Example 4

A composite anode was produced using a mixture of TiO_2 , Al_2O_3 and V_2O_3 in an
20 elemental ratio of Ti-6Al-4V. A stoichiometric ratio of graphite flake was mixed with the oxides and a coal tar pitch binder was used. The molded composite anode was heat treated to 1200°C in an inert atmosphere. The composite anode was placed in the anode basket as described in Example 1 but a sheet of titanium was used as the cathode. The electrolyte

consisted of NaCl-LiCl-KCl eutetic with 20 mole % LiF. Electrolysis was conducted at a cathode current density of 1.25 amps/cm^2 , which produced particles in a size primarily in the range of 10-80 microns. The harvested particles were analyzed and found to contain a ratio of Ti-6Al-4V.

5 Example 5

A composite anode was prepared as described in Example 1 and heat treated to 1150°C . The molten salt electrolyte consisted of KF-NaF-LiF eutectic operated at 650°C . The cathode was nickel metal with electrolysis conducted at a cathode current density of 0.25 amps/cm^2 . A coherent film of titanium 10 microns thick was deposited on the nickel cathode.

10 Example 6

A composite anode was produced as described in Example 2 using Y_2O_3 and graphite flake in stoichiometric ratio. The anode was electrolyzed as in Example 2, which produced yttrium metal in a particle size of 10-30 microns.

Example 7

15 A composite anode was produced as described in Example 2 using stoichiometric ratio of HfO_2 and carbon. Electrolysis of the anode in a molten salt electrolyte, as in Example 4, at a cathode current density of 0.5 amperes/cm^2 produced metal hafnium metal particulate having a particle size of 10 - 100 microns.

Example 8

20 A composite anode was produced by mixing a stoichiometric amount of Cr_2O_3 -C and a pitch binder. The composite anode was heated in the absence of air to 1400°C and then electrolyzed at a cathode current density of 0.25 amps/cm^2 in a molten salt electrolyte as in Example 4. A chromium particulate was produced having a particle size of 5-40 microns.

Example 9

Rutile ore which contained approximately 95% TiO_2 was dried and mixed with graphite flake and a resin binder to produce the oxide-carbon in stoichiometric ratio. The mixture was compressed to 20,000 psi and heat treated in an inert atmosphere to 1200°C. The anode was electrolyzed as in Example 4, which produced a powder at the cathode containing primarily titanium, and small amounts of iron, aluminum, niobium, vanadium and silicon having a particle size of 1 - 80 microns.

Example 10

A salt composition of (65 AlCl_3 – 35 NaCl mole %) -20 mole % NaF was utilized as the electrolyte at an operating temperature of 190°C. A composite anode was utilized as described in Example 1 with electrolysis conducted with a pulsed current 3 seconds on and 1 second off. A crystalline titanium deposit of flake morphology was produced at a cathode current density of 1 amps/cm^2 .

Example 11

Example 10 was repeated with a cathode current density of 0.25 amps/cm^2 . The resulting titanium deposit was a solid film on the cathode. The pulse scheme was then modified to 3 seconds on ¼ second off with periodic reverse polarity and then repeating the cycle. The deposit was a solid film with a very fine grain microstructure. Other shape form pulses provided similar results.

Example 12

Hydrogen was used at the cathode in an electrolytic cell similar to Example 10 with or without a pulsed current. Cell voltage was decreased by about 10 to 15%, and titanium hydride powder formed in-situ in the cell instead of metallic titanium powder. Washing the

titanium hydride produced oxygen pick up of ≤ 200 ppm. The resulting titanium hydride was then dehydrogenated by heating to about 650°C to produce metallic titanium powder with ≤ 400 ppm oxygen. This oxygen level is an order of magnitude lower than titanium powder produced by any other process.

5

Example 13

Titanium oxide was mixed with a stoichiometric amount of carbon black and heated under a reduced pressure of 0.01 atmosphere in argon to a temperature of 1450°C which produced the titanium suboxide of Ti_2O_3 with no other suboxides or contaminants such as TiC . The Ti_2O_3 was mixed with graphite flake, a binder of phenobitic resin, and pressed into a
10 block. The block was heated in the absence of air to 1100°C which formed an anode. The resulting composite anode was used in a fused salt consisting of the eutectic of LiCl-KCl operated at 500°C . Electrolysis was conducted in trial one at 1 amp/cm^2 on the cathode which produced titanium particulate in a size of 1 to 10 microns. In a second trial a titanium
15 sponge was placed in the bottom of the fused salt and TiCl_4 was bubbled onto the sponge which produced TiCl_2 in the salt bath. TiCl_4 continued until a concentration of 5% TiCl_2 was generated. Electrolysis was then performed as in trial one and titanium particulate with a size up to 400 microns was produced, thus showing with a titanium ion in solution larger size titanium particulate was produced.

Example 14

20 An identical system as in Example 13 was created before and TiCl_2 was generated, and in trial one the electrolysis was performed at 40 amps/cm^2 . The titanium particulate produced was in a size range of 20 to 100 microns. In trial two electrolysis was performed at 125 amps/cm^2 which produced titanium particles in approximately the same size as the 40

amps/cm² current density trial. In trial three electrolysis was also performed at 125 amps/cm² with argon gas bubbling over the cathode to create a large mass flow. The titanium particulate produced in the high mass flow at 125 amps/cm² was in the size range of 40 to 200 microns. The titanium suboxide-carbon composite anode provides the opportunity to
5 operate at very high cathode current densities and in a high mass flow regime.

Example 15

TiO₂ and carbon were heated under a pressure of 0.01 residual argon atmosphere to 1850°C which produced TiO and CO. The TiO was mixed with stoichiometric carbon and a binder and molded into a block which was heated to 1100°C which formed a composite
10 anode. The resulting composite anode was placed in a salt mixture of 60NaCl-40MgCl₂ and 20 mole percent NaF based on the chloride salt mixture operated at 600°C. In trial one the electrolysis was performed at 0.15 amps/cm² and titanium particulate in the size range of 50 to 300 microns was produced. In trial two, a titanium sponge was placed in a small crucible immersed in the salt bath and TiCl₄ was bubbled onto the sponge that produced TiCl₂ until the
15 concentration was 8% TiCl₂ in the salt. Electrolysis was performed at 0.15 amps/cm² which produced titanium particulate in the 200 to 500 micron size. The oxygen content was 380 parts per million.

Example 16

Rutile with a composition as follows, and the remainder titanium was processed as shown in the headings:

Impurities	Units	As received composition	After heating to 1700°C with carbon	Purity of Electrolytically produced titanium
Al	ppm	5300	4200	700
Ca	ppm	570	530	<100
Cr	ppm	300	150	100
Fe	ppm	4390	140	100
Mg	ppm	1470	1270	500
Si	ppm	12000	<100	<100
V	ppm	2290	2290	2000
Zr	ppm	360	250	300

With the remainder titanium

- 5 The rutile was mixed with carbon in a ratio of 1.1 to stoichiometry and heated to 1700°C in argon at atmospheric pressure. The composition after heating is shown in the second column which shows the rutile was purified and particularly in the case of iron and silicon of which the latter is most undesirable as an impurity in titanium metal.

- The purified rutile was mixed with carbon and resin and molded onto a block which
- 10 was heat treated to 1250°C. The composite block was utilized as an anode in a salt bath of NaCl-CaCl₂ operated at 650°C. Electrolysis was performed at 0.5 amps/cm² which produced particulate in the size range of 50-350 microns with a purity as shown in column five above. Aluminum and vanadium are desirable alloying elements for titanium and are used in most titanium alloys. Thus a relatively pure titanium is produced from low cost domestic source
- 15 rutile which can meet virtually all market demands except the stringent aerospace requirements.

Example 17

TiO₂ was mixed with carbon and heated in a 90% nitrogen 10% hydrogen atmosphere to 1600⁰C which produced titanium nitride (TiN). The TiN was pressed and sintered at 2000⁰C in a nitrogen atmosphere. The TiN block was used as an anode in a salt mixture of (NaCl-KCl) - 20 mole % NaF operated at 700⁰C. Electrolysis was conducted at 0.5 amps/cm² which produced titanium particulate in the size range of 20 to 350 microns and nitrogen gas was given off at the anode.

Example 18

TiO₂ was mixed with carbon in a ratio of 1 to 1.5 over stoichiometry and heated in argon at 1600⁰C which produced titanium carbide (TiC). The TiC was pressed and sintered at 2000⁰C. The TiC was used as an anode in the same salt as in Example 17. During electrolysis at 1 amp/cm² oxygen was bubbled under the TiC anode in an amount equivalent to the current to produce titanium so that the oxygen reacted with the freed carbon to produce CO₂/CO which is often referred to as depolarizing the electrode. A diaphragm of porous alumina was placed between the anode and cathode to prevent any oxygen from contacting the deposited titanium particulate and oxidizing it. The particle size of titanium particulate produced was in the size range of 20 to 200 microns.

Example 19

The suboxide TiO was produced by reacting TiO₂ with stoichiometric carbon in a vacuum of 0.01 atmosphere at a temperature of 1850⁰C. The TiO was then pressed and practically sintered at 1450⁰C to provide a porous body which served as a cathode in a fused salt bath of calcium chloride containing 5% calcium oxide operated at 900⁰C. A graphite anode was utilized and electrolysis performed at a constant voltage of 3.0V for a

period of 12 hours. The TiO was reduced to titanium metal with oxygen being attracted to the anode to produce CO₂/CO.

Example 20

Example 19 was repeated using Ti₂O₃ as the starting material.

5

Example 21

Example 19 was repeated with the exception the electrolyte was the eutectic of CaCl₂-NaCl which was operated at 750⁰C. With the suboxide TiO, the lower temperature salt bath can be used to reduce TiO to titanium metal.

Example 22

10

The molten salt bath electrolyte of CaCl₂ operated at 900⁰C showed a considerable solubility of the reduced suboxide of titanium TiO. In a salt bath operated at 900⁰C 5 wt % TiO was added and electrolysis conducted with a carbon anode. Titanium particulate was deposited on the cathode at a current density of 1 amp/cm². In a second trial a porous alumina diaphragm was used around the anode to prevent any oxygen from diffusing to the deposited titanium on the cathode and contaminating the deposited titanium particulate.

15

Example 23

A molten salt composition consisting of the CaCl₂-NaCl eutectic containing 20 mole % NaF was operated at 750⁰C and 2 wt % TiO was added which became soluble in the salt bath. A carbon anode was used and electrolysis performed at a cathode current density of 0.25 amps/cm². Titanium particulate was deposited on the cathode and CO₂ /CO was evolved from the carbon anode.

20

Example 24

TiO was produced as described in Example 15 and mixed with carbon particulate.

The mixture of TiO-C was placed in a porous carbon-carbon basket which served as the anode electrical conductor. The anode basket containing TiO-C was placed in a salt of LiCl-KCl eutectic containing 20 wt% NaF operated at 680°C. Electrolysis was performed at 1 amps/cm² which produced titanium particularate in the size range of 50-500 microns which demonstrated a physical mixture of TiO-C can serve as an anode.

Example 25

An anode produced as described in Example 13 was utilized in the electrolyte given in Example 13 with electrolysis conducted at 1 amps/cm² concurrent with hydrogen bubbling under the cathode. The deposit was titanium particularate in the size range of 50-800 microns. Heating the deposit showed hydrogen evolution as detected in a mass spectrometer.

Example 26

A graphite crucible was set inside a steel cell with a cover and seal to provide an inert atmosphere with an argon purge. A graphite rod with a reduced tip to serve as a resistor was placed through a standard feed-through in the cell cover. Calcium fluoride was placed in the graphite crucible. The graphite rod was heated resistively between a connection to it and the steel cell which raised the temperature to 1700°C which melted the calcium fluoride. TiO was then added at 5 wt%. Electrolysis was conducted at 1 amps/cm² between a separate graphite anode and the crucible serving as the cathode. After six hours of electrolysis the experiment was stopped and the system cooled. Breaking the salt revealed beads of titanium that had been produced in the molten salt.

The above embodiments and examples are given to illustrate the scope and spirit of the instant invention. These embodiments and examples are within the contemplation of the

present invention. Therefore, the present invention should be limited only by the appended claims.